

# Specification Elastoseal

1999/03/15

English

<u>Physiical properties )</u>	<u>Unit</u>	<u>Requirements</u>	<u>Test methods</u>
Hardness	°IRH	60 ± 5	BS 903 A26
Modulus at 300% elongation	Mpa	min 4,0	BS 903 A2
Tensile Strength	Mpa	min 7,0	BS 903 A2
Elongation at break	%	min 300	BS 903 A2
Tear Strength	kN/m	min 30	BS 903 A3 C
Properties after ageing 168h/121°C			BS 903 A19
Tensile Strength	Mpa	min 5,0	BS 903 A2
Elongation at break	%	min 250	BS 903 A2
Brittle point	C°	max.-30	BS 903 A25

## Additional requirements

Approvals

Thickness

Nominal ±10%

Identification

Each roll marked with productname, article- and roll number,dimensions, date of manufacture and signature.

Packing

Polyethylene-film wrapping